

QC10 F

Rapid Set Flowable Concrete

APPLICATIONS

QC10 F is a specially formulated, two-part, polymer and fiber-modified concrete designed for backfilling around manhole frames and catch basins. It is also suitable for surface repairs on bridge decks. Engineered to perform in low-temperatures, QC10F ensures durability and reliability in challenging environments.



TECHNICAL

QC10 F contains special cements and graded aggregate, the product requires only the addition of water on site to form a high strength concrete. QC10 F is suitable for applications from 1" to 8" in one pass.

PREPARATION

All surfaces should be free from oil, grease, dust or any other visible contaminants. Remove all loose particles and work on a sound substrate. Pre-soak the area with clean water prior to application to aid bond. Remove ponded water before applying the product. Good concrete practice should always be observed to enable the mix to be placed into position within 4 minutes.

MIXING

QC10 F can be mixed mechanically or by hand. If by hand, ensure that the mixing is vigorous. Mix the inner bag containing the cement with the sand/aggregate. QC10 F is formulated to be mixed to a smooth flowable consistency. It is advisable to add a maximum of 1.89 litres of water initially, mix and if required, add up to a further 0.95 liters. Note: It is essential that this product not be over-watered. The addition of excessive water will result in slower strength gain, reduced final compressive strength and the possibility of shrinkage cracking. Sand/aggregate contains moisture and the volume of water required will vary depending on the moisture content of the aggregate. Mix only enough material to apply within 4 minutes. Never remix or add water. If the product needs to be applied to walls then the water content can be reduced to obtain a stiffer consistency.

PLACING

QC10 F should be poured into place (if required lightly trowel to ensure good contact with edges) 2" below the required surface. Once the material has reached an initial set, horizontal surfaces of the reinstatement, including the ironwork, should be sprayed with Instamac SCJ. This will prevent the ingress of water into the reinstatement and promote a good bond. Ensure all vertical substrates are fully covered. Clean any mixing equipment with water immediately after use.

STORAGE

Store in closed original container at temperatures between 5°C and 30°C. Avoid frost. This product must be stored in unopened bags, clear of the ground in cool, dry conditions and protected from excessive drafts. If stored correctly and used within 24 months of the date shown on the bag, the activity of the reducing agent will be maintained and this product will contain, when mixed with water, no more than 0.0002% soluble Chromium (VI) of the total dry weight of the cement.

SHELF LIFE

Shelf life from date of manufacture in correct conditions for sealed packaging is 24 months. Note: The use of this product after the end of the declared storage period may increase the risk of an allergic reaction. High temperatures and high humidity will lead to a reduced shelf life.

HEALTH, SAFETY AND ENVIRONMENTAL

Please ensure that appropriate PPE is used when preparing, mixing and applying products. Always wash your hands before consuming food and make sure that materials are kept safely out of reach of children and animals. Please dispose of packaging and waste responsibly and in accordance with local municipality requirements. A full material datasheet relating to this product is available from Da-Lee.

All products are sold subject to our conditions of sale, copies of which may be obtained on request.

QUALITY ASSURANCE

All products are manufactured in a plant whose quality management system is certified / registered as being in conformity with BS EN ISO 9001. Our products are guaranteed against defective materials and manufacture, and will be replaced or money refunded if the goods do not comply with our promotional literature. We cannot however accept any liability arising from the application or use of our products because we have no direct or continuous control over where and how our products are used.



New York State DOT Bridge Deck Repairs

TECHNICAL DATA

Compressive strength (PSI)	
60 minutes	3000
1 day	5000
7 days	7250
28 days	9000
Tensile strength (PSI)	
1 day	220
7 days	360
28 days	435
Flexural strength (PSI)	
1 day	650
7 days	725
28 days	870
Workability*	5-10 minutes
Set time*	10-20 minutes
Density	1750/Cubic ft
Coverage	2.36 bags per ft ³
Colour	Grey
As with all raw materials, colour variation may occur. This does not affect the consistency or characteristics of the product.	
Unit/Packaging	55lbs/25kg plastic bag (56 units per pallet)

*Depending on temperatures - tests carried out at 68°F
Cool temperatures retard, warm temperatures accelerate product performance.

Contact Us

Da-Lee Group, 350 Jones Road, Stoney Creek, ON L8E 5N2, Canada
Tel: 905 643 1135 Email: contact@daleegroup.com Website: daleegroup.com